

Everlac Anti-Slip Aggregate

Technical
Data Sheet
Number 23

Everlac Anti-Slip Aggregate has been specifically formulated for incorporation into **Everlac**'s range of specialist floor coatings to improve surface slip resistance.

PURPOSE

Everlac Anti-Slip Aggregate has been specifically formulated for incorporation into **Everlac**'s range of specialist floor coatings such as **Everlac** Moisture Cure Polyurethane, **Everlac** Epoxy Floor Paint, **Everseal** Extra and **Everthane** to increase safety by improving surface slip resistance particularly when the surface is wet.

METHOD OF APPLICATION

The method of incorporation will vary dependent on the floor coating type:

Everlac Epoxy Floor Paint, **Everseal** Extra and **Everthane**

For these products **Everlac** Anti-Slip Aggregate should be incorporated slowly into the coating mixture with continuous stirring. Once incorporated care should be taken to ensure that settlement does not take place within the coating by regular agitation of the mixture.

1kg of **Everlac** Anti-Slip aggregate should be incorporated, in the final coat, for every 5 litre of coating Mixture.

Everlac Moisture Cure Polyurethane

Everlac Anti-Slip Aggregate should not be incorporated within the coating mixture but should be scattered manually or ideally blown over the wet surface with a hopper gun at 50-100m²/kg.

SPECIAL PROPERTIES

- Improves slip resistance particularly on wet surfaces.

TECHNICAL DATA

COVERAGE – For incorporation within the coating mixture – 1kg to every 5 litres

For surface scatter between 50-100 m²/kg

COLOUR AND APPEARANCE – Off white and angular

HARDNESS – Very hard (9 MOHS)

SPECIFIC GRAVITY – 3.85

PACKAGING - 1 and 5 kg plastic buckets.

HEALTH & SAFETY – **Everlac** Anti-Slip Aggregate
Wear disposable gloves and eye protection to handle.

A Material Safety Data Sheet is available on request.